

TECHNICAL PROPERTY / PARAMETER	VALUE / SPECIFICATION	UNIT / TEST METHOD / REMARKS
GENERAL INFORMATION		
Material Category	Limestone Flooring	Natural Stone Collection
Surface Finish	Antique	Surface Treatment Type
DIMENSIONS & WEIGHT		
Weight per Square Meter	50 kg/m ² (20mm)	kg/m ² (thickness in mm)
Weight per Square Foot	10 lbs/ft ² (3/4")	lbs/ft ² (thickness in inches)
Thickness Tolerance	±2mm	mm
Dimension Tolerance	±2mm	mm
MECHANICAL & PHYSICAL STRENGTH		
Slip Resistance (Unsealed)	45 Mean BPN/SRV (P4)	Mean BPN/SRV / Classification (AS 4586)
Modulus of Rupture (MoR)	15.3 MPa (Dried) / 12.8 MPa (Soaked)	MPa (Soaked / Dried)
Flexural Strength	Flexural strength loss 19.4% (EN12372)	MPa (Dried / Soaked)
Bulk Specific Gravity	2584 kg/m ³	kg/m ³
Water Absorption (Mean)	1.60% by Weight / 1.74% by Volume	% Mean by Weight / Volume
DURABILITY & WEATHERING EXPOSURE		
Salt Resistance - Unsealed	0.5% (A Grade) / 5.1% (B Grade)	% Mean weight loss (AS/NZS 4456.10)
Salt Resistance - Sealed	0.1% (A Grade)	% Weight loss (Defender CSD50 / SolvSealer Gold)
Weathering / Exposure (Soak/Freeze/Thaw)	Cracking: GB / Erosion: 36.7 / General Appearance: 22.1 / 10 Cycles	ASTM D5722 (Cracking, Erosion, Appearance)
Crystalline Silica Content	0%	% SiO ₂ Content in Rock
OPTICAL & THERMAL PROPERTIES		
Solar Reflectance Index (SRI)	N/A	Solar Reflectance / SRI / Emittance
Light Reflectance Value (LRV)	N/A	% Dry / Wet

TESMAR STONE — CONTACT & HEADQUARTERS INFORMATION

ADDRESS: 9 AVENUE IBN SINA 2EME ETAGE, AGDAL RABAT, MOROCCO
 EMAIL: INFO@TESMARSTONE.COM

PHONE: +212 6 61 29 52 80
 WEBSITE: www.TESMARSTONE.COM