

TECHNICAL PROPERTY / PARAMETER	VALUE / SPECIFICATION	UNIT / TEST METHOD / REMARKS
GENERAL INFORMATION		
Material Category	Limestone Flooring	Natural Stone Collection
Surface Finish	Tumbled	Surface Treatment Type
DIMENSIONS & WEIGHT		
Weight per Square Meter	37 kg/m ² (13mm)	kg/m ² (thickness in mm)
Weight per Square Foot	N/A	lbs/ft ² (thickness in inches)
Thickness Tolerance	±2mm	mm
Dimension Tolerance	+3mm	mm
MECHANICAL & PHYSICAL STRENGTH		
Slip Resistance (Unsealed)	56 Mean BPN/SRV (P5)	Mean BPN/SRV / Classification (AS 4586)
Modulus of Rupture (MoR)	10.8 MPa (Dried) / 7.8 MPa (Soaked)	MPa (Soaked / Dried)
Flexural Strength	54.2 % / 6.4 %	MPa (Dried / Soaked)
Bulk Specific Gravity	2451 kg/m ³	kg/m ³
Water Absorption (Mean)	2.70% by Weight / 6.50% by Volume	% Mean by Weight / Volume
DURABILITY & WEATHERING EXPOSURE		
Salt Resistance - Unsealed	<0.1% (AA Grade) / 2.8% (B Grade)	% Mean weight loss (AS/NZS 4456.10)
Salt Resistance - Sealed	N/A	% Weight loss (Defender CSD50 / SolvSealer Gold)
Weathering / Exposure (Soak/Freeze/Thaw)	10 Cracking / 10 Erosion / 10 General Appearance	ASTM D5722 (Cracking, Erosion, Appearance)
Crystalline Silica Content	45%	% SiO ₂ Content in Rock
OPTICAL & THERMAL PROPERTIES		
Solar Reflectance Index (SRI)	Solar Reflectance: 49-43 / SRI: 32-91 / Reflectance: 0.11 / Emittance: 0.89	Solar Reflectance / SRI / Emittance
Light Reflectance Value (LRV)	N/A	% Dry / Wet

TESMAR STONE — CONTACT & HEADQUARTERS INFORMATION

ADDRESS: 9 AVENUE IBN SINA 2EME ETAGE, AGDAL RABAT, MOROCCO
 EMAIL: INFO@TESMARSTONE.COM

PHONE: +212 6 61 29 52 80
 WEBSITE: www.TESMARSTONE.COM